


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C07C 2/34	A1	(11) International Publication Number: WO 99/55646 (43) International Publication Date: 4 November 1999 (04.11.99)
(21) International Application Number: PCT/IB99/00747 (22) International Filing Date: 26 April 1999 (26.04.99) (30) Priority Data: 98/3539 28 April 1998 (28.04.98) ZA (71)(72) Applicants and Inventors: DE WET, Hester [ZA/ZA]; 24 Beethoven Street, Vanderbijlpark 1911 (ZA). MORGAN, David, Hedley [ZA/ZA]; 2 Saligna Townhouses, Frans Oerder Street, Vanderbijlpark 1911 (ZA). RANWELL, Alta [ZA/ZA]; 54 Beethoven Street, Vanderbijlpark 1911 (ZA). (74) Agent: SCHWEIZER, Adrian; Adams & Adams, P.O. Box 1014, Adams & Adams Place, 1140 Prospect Street, Hatfield, Pretoria 0001 (ZA).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> 

(54) Title: PRODUCTION OF DIMERS**(57) Abstract**

The invention provides a process for the production of dimers from an olefinic feedstock containing α -olefins, by contacting the feedstock with a metallocene/aluminoxane catalyst, thereby selectively to dimerize α -olefins in the feedstock by means of a metallocene-catalyzed dimerization reaction. The feedstock is in the form of a Fischer-Tropsch-derived olefinic feedstock comprising a mixture of Fischer-Tropsch-derived hydrocarbons made up of at most 90 % by mass of α -olefins, at least 5 % by mass of olefins, other than α -olefins, selected from (linear) internal olefins, branched internal olefins, cyclic olefins, dienes, (trienes) and mixtures thereof, and at least 5 % by mass of constituents, other than olefins, selected from paraffins, oxygenated hydrocarbons, aromatic hydrocarbons and mixtures thereof. The metallocene-catalyzed dimerization reaction takes place while the olefins which are dimerized form part of the mixture constituted by the feedstock.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PRODUCTION OF DIMERS

THIS INVENTION relates to a process for the production of dimers from an olefinic feedstock. More particularly, the invention relates to a process suitable for the production of a product having the general
5 formula $R'R''C=CH_2$, in which R' and R'' are alkyl groups, from an olefinic feedstock.

According to the invention there is provided a process for the production of dimers from an olefinic feedstock containing α -olefins, the process comprising contacting the feedstock with a metallocene/
10 aluminoxane catalyst, thereby selectively to dimerize α -olefins in the feedstock by means of a metallocene-catalyzed dimerization reaction, the feedstock being in the form of a Fischer-Tropsch-derived olefinic feedstock comprising a mixture of Fischer-Tropsch-derived hydrocarbons made up of at most 90% by mass of α -olefins, at least 5% by mass of
15 olefins, other than α -olefins, selected from linear internal olefins, branched internal olefins, cyclic olefins, dienes, trienes and mixtures thereof, and at least 5% by mass of constituents, other than olefins, selected from paraffins, oxygenated hydrocarbons, aromatic hydrocarbons and mixtures thereof, the metallocene-catalyzed
20 dimerization reaction taking place while the olefins which are dimerized form part of the mixture constituted by the feedstock.

By a Fischer-Tropsch-derived olefinic feedstock is meant an olefinic feedstock which is a product obtained by subjecting a synthesis gas comprising carbon monoxide and hydrogen to Fischer-Tropsch reaction
25 conditions in the presence of a suitable Fischer-Tropsch catalyst, which

catalyst may be iron-based, cobalt-based or iron/cobalt-based. In particular the Fischer-Tropsch-derived olefinic feedstock may be one which, after production thereof from the synthesis gas, has been subjected to no substantial further treatment, purification or processing thereof to remove unwanted constituents such as non- α -olefins therefrom, other than cutting so that a suitable cut of the Fischer-Tropsch-derived product will typically be selected for use as the feedstock.

The feedstock may comprise 50 - 90% by mass of said α -olefins, for example 60 - 80% by mass thereof; it may comprise 5 - 20% by mass of said olefins other than α -olefins, for example 9 - 16% by mass thereof; and it may comprise 5 - 30% by mass of said constituents other than olefins, for example 13 - 22% by mass thereof.

By way of example, the feedstock may comprise 50% by mass of α -olefins, 20% by mass olefins other than α -olefins, and 30% by mass of constituents other than olefins. The metallocene/aluminoxane catalyst may have an aluminoxane component which is methylaluminoxane, and a metallocene component which is a compound of the general formula $(Cp)_2MY_2$ in which Cp represents a cyclopentadienyl group, M is a metal selected from zirconium, hafnium and titanium, and Y is selected from hydrogen radicals, halogen radicals (preferably chlorine radicals), alkyl groups (preferably methyl groups) and mixtures thereof. The metallocene component preferably comprises a single compound of said formula $(Cp)_2MY_2$, but it may instead comprise a mixture of several said compounds of formula $(Cp)_2MY_2$.

Still more particularly, the feedstock may comprise olefins other than α -olefins which include linear and/or branched internal olefins, cyclic olefins, dienes and trienes, and constituents of the feedstock other than olefins may include paraffins, aromatics and small amounts of oxygenates. There may be an Al:M atomic ratio between aluminium in the aluminosilicate component of the catalyst and the metal M in the metallocene component of the catalyst of 1:1 - 100:1, preferably 40:1 - 80:1, eg 60:1 - 70:1. As the Al:M atomic ratio increases, the degree of conversion and reaction rate increase, while the selectivity with regard to dimer production decreases, while a reducing Al:M atomic ratio reduces the degree of conversion and the reaction rate, and increases the selectivity for dimer production. An optimum or acceptable Al:M atomic ratio may accordingly be selected by routine experimentation, bearing practical and economic considerations in mind.

It is preferred to have the feedstock in a liquid state during the contacting of the catalyst with the feedstock, and the contacting may take place at a reaction temperature, and at a reaction pressure, both of which can vary within broad limits, the reaction time being determined by the period required to obtain a desired degree of conversion. Thus, reaction temperatures of -60°C to 280°C , eg $20 - 120^{\circ}\text{C}$ have been found to be suitable, and absolute reaction pressures of 1 atmosphere or less, up to 500 atmospheres or more, may be used. In a particular case, the feedstock may be in a liquid state during the contacting of the feedstock with the metallocene/aluminosilicate catalyst, the contacting taking place at a reaction temperature of -60°C to 280°C and at an absolute reaction pressure of 1 - 500 atmospheres, usually at or slightly above 1 atmosphere; and in this case the reaction temperature is preferably $20 - 120^{\circ}\text{C}$, the process being carried out under an inert

atmosphere. Once again, routine experimentation may be used to establish optimum or acceptable reaction conditions with regard to temperature, pressure and reaction time.

5 In accordance with the process of the present invention the aluminoxane component of the catalyst, dissolved in an organic solvent (conveniently the organic solvent used in the preparation of the aluminoxane component) may be admixed with a well-stirred suspension of the metallocene component of the catalyst in an organic liquid which may be inert with regard to the metallocene/aluminoxane catalyst, or
10 conveniently may be in the form of the feedstock used for the dimerization reaction. When the feedstock is used to suspend the metallocene component, the dimerization reaction proceeds in earnest as soon as the admixture thereof with the aluminoxane solution becomes substantially homogeneous. The dimerization is conveniently carried out
15 under an inert atmosphere, eg an argon atmosphere, at atmospheric pressure.

The invention will now be described, by way of non-limiting illustration, with reference to the following Examples:

Example 1

20 A metallocene/aluminoxane catalyst was prepared by admixing 3.07 g of a 30% by mass methylaluminoxane solution in toluene with 0.24 g of $(Cp)_2ZrCl_2$ (zirconocene dichloride) with stirring at room temperature for about 15 minutes under argon, that catalyst having an Al:Zr atomic
25 ratio of 66:1.

31.89 g of a Fischer-Tropsch-derived C₇ cut (containing about 74% by mass of 1-heptene) and 44.82 g of a Fischer-Tropsch-derived C₉ cut (containing about 65% by mass of 1-nonene) were admixed with the catalyst under argon in a reaction vessel in the form of a 300 ml flamed-out Schlenk flask, followed by stirring at room temperature and atmospheric pressure under argon for about 4 hours, before being quenched with a 10% by mass solution of hydrochloric acid in methanol. The quenched solution was stirred for a further 30 minutes and was then washed with water and concentrated with regard to dimer reaction product. Gas-chromatographic analysis of the concentrated washed product showed a degree of conversion of >85% and a mole ratio of dimerization and cross-dimerization products of C₁₄:C₁₆:C₁₈ of 1:2:1 where C₁₄ represents the dimerization product of two of the heptene molecules, C₁₈ represents that of two of the nonene molecules, and C₁₆ represents the cross-dimerization product of one of the heptene molecules with one of the nonene molecules.

20

Example 2

Example 1 was repeated using 3.552 g of the methylaluminoxane and 0.22 g of the (Cp)₂ZrCl₂, with 79.19 g of a Fischer-Tropsch-derived C₈ cut (containing about 40% by mass of 1-octene). The gas-chromatographic analysis showed that the degree of conversion to a C₁₆ product was >77%.

25

An advantage of the invention is that the Applicant has discovered that, surprisingly, a high degree of α -olefinic feedstock purity is not required for an-effective dimerization. Instead, a Fischer-Tropsch-derived olefinic feedstock containing substantial proportions of non- α -olefinic constituents may be employed without any substantial treatment, purification or processing thereof, other than the selection of a suitable cut or cuts thereof containing α -olefins predominantly of the desired number or numbers of carbon atoms, to produce dimers of the desired number or numbers of carbon atoms. The dimers in question can be represented by $R'R''C=CH_2$ in which R' and R'' are alkyl groups and may be the same or different, the dimer being formed from the α -olefins $R'=CH_2$ and $R''=CH_2$, R' and R'' each having typically $C_2 - C_{30}$ carbon atoms, preferably $C_5 - C_{10}$ carbon atoms.

The dimer reaction products of the process of the present invention are useful as starting materials for the production, eg by hydroformylation, of oxygenated products such as aldehydes or alcohols, which in turn can be used to make detergents, surfactants or the like.

While the invention is expected to be suitable for use with any Fischer-Tropsch-derived olefinic feedstock, it is expected to be particularly suitable for such feedstock when derived from a high temperature Fischer-Tropsch process carried out at a temperature above 280°C , preferably above 300°C , for example at 330°C , as contrasted with feedstocks derived from low temperature Fischer-Tropsch processes, typically carried out at about 220°C .

CLAIMS:

1. A process for the production of dimers from an olefinic feedstock containing α -olefins, the process comprising contacting the feedstock with a metallocene/aluminoxane catalyst, thereby selectively to dimerize
5 α -olefins in the feedstock by means of a metallocene-catalyzed dimerization reaction, the process being characterized in that the feedstock is in the form of a Fischer-Tropsch-derived olefinic feedstock comprising a mixture of Fischer-Tropsch-derived hydrocarbons made up of at most 90% by mass of α -olefins, at least 5% by mass of
10 olefins, other than α -olefins, selected from linear internal olefins, branched internal olefins, cyclic olefins, dienes, trienes and mixtures thereof, and at least 5% by mass of constituents, other than olefins, selected from paraffins, oxygenated hydrocarbons, aromatic hydrocarbons and mixtures thereof, the metallocene-catalyzed
15 dimerization reaction taking place while the olefins which are dimerized form part of the mixture constituted by the feedstock.
2. A process as claimed in claim 1, characterized in that the feedstock comprises 50 -90% by mass of said α -olefins.
3. A process as claimed in claim 1 or claim 2, characterized in that
20 the feedstock comprises 5 - 20% by mass of said olefins other than α -olefins.
4. A process as claimed in any one of claims 1 - 3 inclusive, characterized in that the feedstock comprises 5 - 30% by mass of said constituents other than olefins.

5. A process as claimed in any one of the preceding claims, characterized in that the metallocene/aluminoxane catalyst has an aluminoxane component which is methylaluminoxane, and a metallocene component which is a compound of the general formula $(Cp)_2MY_2$ in which Cp represents a cyclopentadienyl group, M is a metal selected from zirconium, hafnium and titanium, and Y is selected from hydrogen radicals, halogen radicals, alkyl groups and mixtures thereof.
6. A process as claimed in claim 5, characterized in that the metallocene component comprises a single compound of said formula $(Cp)_2MY_2$.
7. A process as claimed in claim 5 or claim 6, characterized in that there is an Al:M atomic ratio between aluminium in the aluminoxane component of the catalyst and the metal M in the metallocene component of the catalyst of 1:1 - 100:1.
8. A process as claimed in any one of the preceding claims, characterized in that the feedstock is in a liquid state during the contacting of the feedstock with the metallocene/aluminoxane catalyst, the contacting taking place at a reaction temperature of $-60^{\circ}C$ to $280^{\circ}C$ and at an absolute reaction pressure of 1 - 500 atmospheres.
9. A process as claimed in claim 8, characterized in that the reaction temperature is $20 - 120^{\circ}C$, the process being carried out under an inert atmosphere.
10. A process as claimed in claim 1, substantially as described herein with reference to the Examples.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 99/00747

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C07C2/34

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 513 156 A (TABAK SAMUEL A) 23 April 1985	1-10
A	WO 92 15541 A (ETHYL CORP) 17 September 1992	1-10
L, E	WO 98 52888 A (SASOL CHEMICALS EUROP LTD ;SITETYANA PINDIWI (ZA); WET HESTER DE ()) 26 November 1998 see the whole document	1-10

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

6 July 1999

Date of mailing of the international search report

14/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Janus, S

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int'l Application No

PCT/IB 99/00747

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4513156 A	23-04-1985	US 4626415 A	02-12-1986
WO 9215541 A	17-09-1992	US 5087788 A	11-02-1992
		CA 2100055 A,C	05-09-1992
		DE 69209283 D	25-04-1996
		DE 69209283 T	01-08-1996
		EP 0575356 A	29-12-1993
		JP 6504786 T	02-06-1994
WO 9852888 A	26-11-1998	AU 7540998 A	11-12-1998